

OFFICE OF NAVAL RESEARCH

CONTRACT N00014-94-1-0101

R&T CODE 31321075

Technical Report #52

RADICAL POLYMERIZATION OF STYRENE IN THE PRESENCE
OF NITROXYL RADICALS. EXPERIMENTS AND SIMULATIONS.

by

D. Greszta, K. Matyjaszewski, D. Priddy

Published

in the

ACS Polymer Preprints, in press

Carnegie Mellon University
Department of Chemistry
4400 Fifth Avenue
Pittsburgh, PA 15213

June 12, 1996

Reproduction in whole or in part is permitted for any purpose of the United States Government

This document has been approved for public release and sale;
its distribution is unlimited.

19960621 016

DTIC QUALITY INSPECTED 1

| REPORT DOCUMENTATION PAGE | | | Form Approved OMB No. 0704-0188 | |
|--|---|--|------------------------------------|---|
| <small>Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.</small> | | | | |
| 1. AGENCY USE ONLY (Leave blank) | | 2. REPORT DATE | | 3. REPORT TYPE AND DATES COVERED Technical Report #52 |
| 4. TITLE AND SUBTITLE Radical Polymerization of Styrene in the Presence of Nitroxyl Radicals. Experiments and Simulations. | | | | 5. FUNDING NUMBERS N0004-94-1-0101 |
| 6. AUTHOR(S) D. Greszta, K. Matyjaszewski, D. Priddy | | | | |
| 7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Carnegie Mellon University Department of Chemistry 4400 Fifth Avenue Pittsburgh, PA 15213-2683 | | | | 8. PERFORMING ORGANIZATION REPORT NUMBER N0004-94-1-0101 |
| 9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Department of Navy Office of Naval Research 800 North Quincy Street Arlington, VA 22217-5000 | | | | 10. SPONSORING/MONITORING AGENCY REPORT NUMBER Technical Report #52 |
| 11. SUPPLEMENTARY NOTES | | | | |
| 12a. DISTRIBUTION/AVAILABILITY STATEMENT | | | | 12b. DISTRIBUTION CODE |
| 13. ABSTRACT (Maximum 200 words) <p>Polymerization of styrene in the presence of a stable radical TEMPO has been simulated using a Predici simulations package. Based on the experimental data, a kinetic model for the TEMPO-moderated polymerization of styrene has been proposed. It was shown that in order to properly simulate the experimental data, in addition to the reversible cleavage of the TEMPO-polymeric radical adduct, it is necessary to include thermal self-initiation, transfer and irreversible decomposition of intermediate alkoxyamines in the polymerization model. This model, combined with the experimental data and literature values of the rate constants of propagation (k_p), termination (k_t), transfer (k_{trm}), and alkoxyamines decomposition (k_{decomp}), was then employed to estimate kinetic and thermodynamic parameters of the exchange between dormant and active species. The equilibrium constant K was estimated to be around $1 \cdot 10^{-10}$ mol/L, the deactivation rate constant $k_d = 3 \cdot 10^7 \text{ mol}^{-1} \text{ L s}^{-1}$ and the activation rate constant $k_a = 3 \cdot 10^{-3} \text{ mol}^{-1} \text{ L s}^{-1}$ for bulk styrene polymerization at 120°C.</p> | | | | |
| 14. SUBJECT TERMS | | | | 15. NUMBER OF PAGES |
| | | | | 16. PRICE CODE |
| | | | | |
| 17. SECURITY CLASSIFICATION OF REPORT | 18. SECURITY CLASSIFICATION OF THIS PAGE | 19. SECURITY CLASSIFICATION OF ABSTRACT | 20. LIMITATION OF ABSTRACT | |
| | | | | |

GENERAL INSTRUCTIONS FOR COMPLETING SF 298

The Report Documentation Page (RDP) is used in announcing and cataloging reports. It is important that this information be consistent with the rest of the report, particularly the cover and title page. Instructions for filling in each block of the form follow. It is important to *stay within the lines* to meet optical scanning requirements.

Block 1. Agency Use Only (Leave blank).

Block 2. Report Date. Full publication date including day, month, and year, if available (e.g. 1 Jan 88). Must cite at least the year.

Block 3. Type of Report and Dates Covered. State whether report is interim, final, etc. If applicable, enter inclusive report dates (e.g. 10 Jun 87 - 30 Jun 88).

Block 4. Title and Subtitle. A title is taken from the part of the report that provides the most meaningful and complete information. When a report is prepared in more than one volume, repeat the primary title, add volume number, and include subtitle for the specific volume. On classified documents enter the title classification in parentheses.

Block 5. Funding Numbers. To include contract and grant numbers; may include program element number(s), project number(s), task number(s), and work unit number(s). Use the following labels:

| | |
|----------------------|------------------------------|
| C - Contract | PR - Project |
| G - Grant | TA - Task |
| PE - Program Element | WU - Work Unit Accession No. |

Block 6. Author(s). Name(s) of person(s) responsible for writing the report, performing the research, or credited with the content of the report. If editor or compiler, this should follow the name(s).

Block 7. Performing Organization Name(s) and Address(es). Self-explanatory.

Block 8. Performing Organization Report Number. Enter the unique alphanumeric report number(s) assigned by the organization performing the report.

Block 9. Sponsoring/Monitoring Agency Name(s) and Address(es). Self-explanatory.

Block 10. Sponsoring/Monitoring Agency Report Number. (If known)

Block 11. Supplementary Notes. Enter information not included elsewhere such as: Prepared in cooperation with...; Trans. of...; To be published in... When a report is revised, include a statement whether the new report supersedes or supplements the older report.

Block 12a. Distribution/Availability Statement. Denotes public availability or limitations. Cite any availability to the public. Enter additional limitations or special markings in all capitals (e.g. NOFORN, REL, ITAR).

DOD - See DoDD 5230.24, "Distribution Statements on Technical Documents."

DOE - See authorities.

NASA - See Handbook NHB 2200.2.

NTIS - Leave blank.

Block 12b. Distribution Code.

DOD - Leave blank.

DOE - Enter DOE distribution categories from the Standard Distribution for Unclassified Scientific and Technical Reports.

NASA - Leave blank.

NTIS - Leave blank.

Block 13. Abstract. Include a brief (*Maximum 200 words*) factual summary of the most significant information contained in the report.

Block 14. Subject Terms. Keywords or phrases identifying major subjects in the report.

Block 15. Number of Pages. Enter the total number of pages.

Block 16. Price Code. Enter appropriate price code (*NTIS only*).

Blocks 17 - 19. Security Classifications. Self-explanatory. Enter U.S. Security Classification in accordance with U.S. Security Regulations (i.e., UNCLASSIFIED). If form contains classified information, stamp classification on the top and bottom of the page.

Block 20. Limitation of Abstract. This block must be completed to assign a limitation to the abstract. Enter either UL (unlimited) or SAR (same as report). An entry in this block is necessary if the abstract is to be limited. If blank, the abstract is assumed to be unlimited.

Radical Polymerization of Styrene in the Presence of Nitroxyl Radicals. Experiments and Simulations.

Dorota Greszta, Krzysztof Matyjaszewski*, Carnegie Mellon University,
4400 Fifth Ave., Pittsburgh, PA 15213
Duane Priddy, Dow Plastics, Dow Chemicals Co., Midland, MI 48667

Introduction


Radical polymerization, in spite of its commercial importance, has been very difficult to control at a level attained for anionic and cationic polymerization. A rational design and approach to controlled/living radical polymerization based on the reversible formation of growing radicals from various types of dormant species, has been presented only very recently¹. Use of a stable radical TEMPO (2,2,6,6-tetramethyl-1-piperidinyl-oxy) and corresponding alkoxyamines as moderators for radical polymerization of styrenes has been probably most extensively studied²⁻⁷ but the exact mechanism and reasons for the preparation of well defined polymers are still obscure. The objective of this paper is to summarize experimental data obtained in different but comparable systems and provide a comprehensive view on the polymerization of styrene in the presence of TEMPO. By using computer simulations, effects of various reactions occurring in this system, including self-initiation, termination, transfer, decomposition of alkoxyamines, as well as dynamics of exchange on kinetics, molecular weights and polydispersities are analyzed.

Simulations were performed using program PREDICI which is based on a adaptive Rothe method⁸ as a new numerical strategy for time discretization. It uses a discrete Galerkin h-p method to represent chain length distribution and allows to follow concentration of all substrates, low and high molecular weight products and intermediates as well as molecular weights and the corresponding distributions of all types of macromolecules



Elementary Reactions Involved In TEMPO Mediated Styrene Polymerization

The simplest system for the TEMPO mediated styrene polymerization includes styrene and the corresponding TEMPO adduct, 2,2,6,6-tetramethyl-1-(1-phenylethoxy)piperidine, MT. The basic reactions in such system include:

- homolytic cleavage of the adduct:




- initiation and subsequent propagation:




To simplify the analysis it is assumed that $k_{p1}=k_{pn}=k_p$. Values of propagation rate constants are available in literature and they are $k_p=2 \cdot 10^3$ mol⁻¹·L·s⁻¹ at 120°C⁹.


- reversible deactivation of active chains:



- termination with a rate constant $k_t = 10^7 \text{ mol}^{-1} \cdot \text{L} \cdot \text{s}^{-1}$ at 120°C 10



- thermal initiation, presumably by formation of unsaturated dimers¹¹



The rate of thermal formation of dimer has been determined by using various inhibitors. By extrapolation of the data available in literature^{12,13} the rate of dimer formation at 120°C was estimated to be approximately $1 \cdot 10^{-6} \text{ mol} \cdot \text{L}^{-1}$. From this value $k_{\text{dim}} = 1 \cdot 10^{-8} \text{ mol} \cdot \text{L}^{-1} \cdot \text{s}^{-1}$ was calculated.


From this value $k_{\text{dim}} = 1 \cdot 10^{-8} \text{ mol}^{-1} \cdot \text{L} \cdot \text{s}^{-1}$ was calculated. The actual initiation probably occurs via hydrogen atom transfer to monomer as shown in Equation 7.



There is no literature data about this step of thermal initiation. In order to fit the experimental kinetic data $k_i = 3 \cdot 10^{-8} \text{ mol}^{-1} \cdot \text{L} \cdot \text{s}^{-1}$ was used. Additionally it was assumed that the dimer radical D^* reacts with monomer with the same rate constant as monomeric radical.


Although the simulations with the model based on equations 1-7 fit the experimental kinetic data very well, the calculated molecular weights were 100 times too high. In order to fit the molecular weights, a transfer to monomer was added to the model. However, it did not result in a significant

decrease of molecular weights (at 120 °C $C_{\text{TM}}=1.4 \cdot 10^{-4}$ l, $k_{\text{TM}}=0.28$ mol-
l.L s⁻¹).





Because most polymerizations were studied only to moderate conversions (<70%), transfer to polymer was not taken into account in these simulation.

When a transfer to the Mayo dimer (Eq. 9) was incorporated into the model, a good agreement between observed and calculated molecular weights was obtained. The optimum fit was achieved for $k_{trD}=50 \text{ mol}^{-1}\text{L}^{-1}\text{s}^{-1}$. This relatively large value is justified as suggested by Olaj and coworkers¹⁵.



It has been reported that the adduct spontaneously thermally decomposes to styrene and hydroxylamine¹⁶ (Eq. 10). Macromolecular species should decompose with the similar rate constant $k_{\text{decomp}} = 3.10 \cdot 10^{-5} \text{ s}^{-1}$ at 120 °C (Eq. 11).



Results and Discussion:

Kinetics of polymerization

Figure 1 illustrates a simulated kinetics of thermal self-initiated polymerization of styrene, together with a simulated kinetics of polymerization in the presence of 2,2,6,6-tetramethyl-1-(1-phenylethoxy) piperidine and with experimental data from literature on polymerization initiated by AIBN or BPO and TEMPO or its adduct at 120 °C.




Figure 1. Kinetic plots for the simulated polymerization of styrene in the presence of adduct (0.012M) in bulk at 120°C with variable kinetics and thermodynamics of exchange, simulated thermal polymerization of styrene and experimental data for different adduct concentrations: **a**: $K=1\cdot10^{-9}$, $k_p=1\cdot10^9$, $k_a=1\cdot10^9$; **b**: $K=1\cdot10^{-10}$, $k_p=1\cdot10^7$, $k_a=1\cdot10^{-3}$; **c**: $K=1\cdot10^{-10}$, $k_p=1\cdot10^9$, $k_a=1\cdot10^{-1}$; **d**: $K=1\cdot10^{-11}$, $k_p=1\cdot10^9$, $k_a=1\cdot10^{-2}$; **e**: thermal polymerization; exp. data: **x** [adduct]=0.012M; **+** [adduct]=0.009M; **Δ** [adduct]=0.003M¹⁷; **○** [adduct]=0M; **□** [adduct]=0.010M¹⁸; **●** [AIBN]=[TEMPO]=0.010M⁵; **•** [BPO]=[TEMPO]=0.010M^{3,19}; (K is in mol/L, k_p is in mol⁻¹·L·s⁻¹ and k_a in s⁻¹)

The best fit to experimental kinetic data, was found for values of the equilibrium constant $K=k_a/k_d \leq 10^{-10} \text{ mol/L}$, preferably $K=10^{-11} \text{ mol/L}$. Apparently the dynamics of exchange has no effect on kinetics. Using either upper limit of the rate constants of deactivation $k_d=10^9 \text{ mol}^{-1} \cdot \text{L} \cdot \text{s}^{-1}$ or 100 times lower values $k_d=10^7 \text{ mol}^{-1} \cdot \text{L} \cdot \text{s}^{-1}$ (and correspondingly $k_a=10^{-15} \text{ s}^{-1}$ and 10^{-3} s^{-1}) has no effect on the rate of monomer consumption. $K=10^{-10} \text{ mol/L}$ is the upper limit for the equilibrium constant and lower values such as 10^{-11} mol/L also fit the observed kinetics.

Equilibrium TEMPO concentrations

The available literature data and also estimates by UV and EPR indicate that approximately 1 to 10% of TEMPO (based on the initial alkoxyamine) is formed in the reaction^{5,20}. The simulations showed that such high concentration of TEMPO is possible only in a system with the equilibrium constant K not lower than 10^{-10} mol/L at 120°C. Thus taking this into account as well as the results from kinetics simulations, the equilibrium constant K should be $\approx 10^{-10}$ mol/L.

Evolution of molecular weights and polydispersities with conversion.

No transfer, no decomposition

Figure 2 illustrates the evolution of molecular weights with conversion for the simplest systems without transfer and decomposition with variable exchange rates but constant value $K=10^{-10}$ mol/L. It seems that some of the reported data agree relatively well with simulations if the rate of activation is larger than $k_a > 10^{-3} \text{ s}^{-1}$ ($k_d > 10^7 \text{ mol}^{-1} \cdot \text{L} \cdot \text{s}^{-1}$). Too high initial molecular weight are predicted for smaller values of the exchange rate constants.




Figure 2. Simulated dependence of number average degree of polymerization on conversion in systems with variable kinetics and equilibrium constant $K=10^{-10}$ mol/L: a: $k_d=1 \cdot 10^9$, $k_a=1 \cdot 10^{-1}$; b: $k_d=1 \cdot 10^8$, $k_a=1 \cdot 10^{-2}$; c: $k_d=1 \cdot 10^7$, $k_a=1 \cdot 10^{-3}$. Solid points correspond to experimental data (c.f. Fig. 1) (k_d is in $\text{mol}^{-1} \cdot \text{L} \cdot \text{s}^{-1}$ and k_a in s^{-1}).

Figure 3 depicts variation of polydispersities with conversion for various values of rate constants of activation and deactivation. The initial best fit was found for $k_d=3 \cdot 10^7 \text{ mol}^{-1} \cdot \text{L} \cdot \text{s}^{-1}$, a value which is substantially lower than the expected diffusion controlled values $k_d=10^9 \text{ mol}^{-1} \cdot \text{L} \cdot \text{s}^{-1}$. This can be ascribed either to higher viscosity of the system or to steric effects decreasing the reactivity of a macroradical. In systems with slow exchange a monotonous decrease of polydispersity with conversion is expected. The observed polydispersities increase at higher conversions. Thus some additional side reactions contribute to the broadening of molecular weight distribution.




Figure 3. Simulated dependence of molecular weight distributions on conversion in systems with variable kinetics and equilibrium constant $K=10^{-10}$ mol/L: a: $k_d=1 \cdot 10^9$, $k_a=1 \cdot 10^{-1}$; b: $k_d=3 \cdot 10^7$, $k_a=3 \cdot 10^{-3}$; c: $k_d=1 \cdot 10^7$, $k_a=1 \cdot 10^{-3}$ (k_d is in $\text{mol}^{-1} \cdot \text{L} \cdot \text{s}^{-1}$ and k_a in s^{-1}). Solid points correspond to experimental data (c.f. Fig. 1).

Transfer to monomer and decomposition of alkoxyamines

Figure 4 demonstrates the effect of thermal self-initiation, transfer to monomer and decomposition of alkoxyamines on molecular weight distribution. Both self-initiation and transfer lead to relatively small increase of polydispersities, lower than experimentally observed. However, larger, and much closer to those observed experimentally, polydispersities are predicted by taking into account the decomposition reaction (eq. 10 and 11).

In summary, it seems that the values of rate constants used in this work lead to successful simulation of observed rates, molecular weights and polydispersities of obtained of polymers and TEMPO concentrations. Thus, the apparently simple polymerization of styrene moderated by TEMPO adducts includes several other reactions: self-initiation, termination, transfer and decomposition of alkoxyamines.




Figure 4. Effect of various side reactions on simulated dependence of molecular weights distributions on conversion in systems with $K=10^{-10}$ mol/L, $k_d=1 \cdot 10^9 \text{ mol}^{-1} \cdot \text{L} \cdot \text{s}^{-1}$, $k_a=1 \cdot 10^{-1} \text{ s}^{-1}$: a: exchange only; b: thermal initiation; c: transfer to monomer; d: decomposition of alkoxyamine; e: all side reactions combined. Solid points correspond to experimental data (c.f. Fig. 1).

Conclusions

TEMPO moderated polymerization of styrene proceeds with the very low stationary concentration of radicals generated by homolytic cleavage of alkoxyamines. Polymerization rates in the absence and in the presence of variable concentrations of alkoxyamines are nearly the same, indicating that majority of radicals are produced by self initiation. The equilibrium constant of reversible cleavage of alkoxyamines at 120°C is $K=10^{-10}$ mol/L as estimated from kinetics and concentration of TEMPO observed in the polymerization. Rate constant of activation (cleavage) of alkoxyamines is in the range of $k_a=3 \cdot 10^{-3} \text{ s}^{-1}$. Correspondingly, rate constant of deactivation (reaction of growing radicals with TEMPO) is in the range of $k_d=3 \cdot 10^7 \text{ mol}^{-1} \cdot \text{L} \cdot \text{s}^{-1}$. In addition to self-initiation, propagation, exchange and termination, other side reactions such as transfer and decomposition of alkoxyamines are also present.

Acknowledgement:

This work was partially supported by a grant from Office of Naval Research.

References:

- Greszta, D.; Mardare, D.; Matyjaszewski, K. *Macromolecules* 1994, 27, 638.
- Solomon, D. H.; Waverly, G.; Rizzardo, E.; Hill, W.; Cacioli, P. *U. S. Pat.* 4, 581, 429 1986.
- Georges, M. K.; Veregin, R. P. N.; Kazmaier, P. M.; Hamer, G. K. *Polym. Mater. Sci. Eng.* 1993, 68, 6.
- Hawker, C. J. *J. Am. Chem. Soc.* 1994, 116, 11185.
- Matyjaszewski, K.; Gaynor, S.; Greszta, D.; Mardare, D.; Shigemoto, T. *Macromol. Symp.* 1995, 98, 73.
- Catala, J. M.; Bubel, F.; Hammouch, S. O. *Macromolecules* 1995, 28, 8441.
- Li, I.; Howell, B. A.; Ellaboudy, A.; Kastl, P. E.; Priddy, D. B. *ASC Polym. Prepr.* 1995, 36, 469.
- Wulkow, M. *IMPACT Comput. Eng. Sci.* 1992, 4, 153.
- Buback, M.; Gilbert, R. G.; Hutchinson, R. A.; Klumperman, B.; Kuchta, F.-D.; Manders, B. G.; O'Driscoll, K. F.; Russell, G. T.; Schweer, J. *Macromol. Chem. Phys.* 1995, 196, 3267.
- Yamada, B.; Kageoka, M.; Otsu, T. *Macromolecules* 1991, 24, 5234.
- Mayo, F. R. *J. Am. Chem. Soc.* 1953, 75, 6133.
- Russell, K. E.; Tobolsky, A. V. *J. Am. Chem. Soc.* 1953, 75, 5052.
- Buzanowski, W. C.; Graham, J. D.; Priddy, D. B.; Shero, E. *Polymer* 1992, 33, 3055.
- Saha, N. G.; Nandi, U. S. *J. Chem. Soc.* 1958, 12.
- Olaj, O. F.; Kauffmann, H. F.; Breitenbach, J. W. *Makromol. Chem.* 1977, 178, 2707.
- Li, I.; Howell, B. A.; Matyjaszewski, K.; Shigemoto, T.; Smith, P. B.; Priddy, D. B. *Macromolecules* 1995, 28, 6692.
- Matyjaszewski, K.; Shigemoto, T. unpublished results.
- Odeh, P. G.; Veregin, R. P. N.; Michalak, L. M.; Brousmiche, D.; Georges, M. K. *Macromolecules* 1995, 28, 8453.
- Matyjaszewski, K.; Gaynor, S.; Greszta, D.; Mardare, D.; Shigemoto, T. *J. Phys. Org. Chem.* 1995, 8, 306.